

**Quality :** ARTEX-260  
**Fabric Weight :** 260gsm  
**Composition :** 93% Meta-Aramid, 5% Para-Aramid, 2% Antistatic  
**Useable Width :** 150cm  
**Nominal Length :** 100cm  
**Weave :** Twill 2/1  
**Application :** Workwear jackets, trousers and coveralls

**Washing Instructions :** 

Do not bleach, do not boil, do not use soap based products only detergents



### Physical Properties

	Warp	Weft
Tensile Strength: (BS EN ISO 13934-1:1999)	1400 N	880 N
Tear Strength: (BS EN ISO 13937-2:2000)	54 N	43 N
Washing Shrinkage: (ISO 5077 after 5 washes ISO 15797)	3%	3%
Abrasion Resistance: (12kPa) (BS EN ISO 12947-2:1999)	-	-
Pilling Resistance: (BS EN ISO 12945-2:2001)	-	-

### Other Properties

<b>Flame retardant</b>	EN ISO 11611 Class 1 EN ISO 11612 A1 & A2, B1, C1, F1
<b>Anti static</b>	EN 1149-5 (1149-3 method 2)

### Colour Fastness

#### Wash Fastness BS EN ISO 105-C06: Method E2S (95°C)

Colour Change	4--5
Colour Staining	4--5

#### Rub Fastness BS EN ISO 105-X12:1995

Wet	4--5
Dry	4

#### Light Fastness BS EN 20105/ISO 105-B02

Light Fastness	4
----------------	---

The data quoted is based upon specific materials and tested by sources believed to be reliable and XM Textiles make no guarantee, express or implied as to use, handling or possession of its products.

Authorised by: XM Quality control department

Date: January 15, 2018

These values are for guidance only, some colours will be better others worse.

Please contact your XM Textiles representative for specific shade details.

XM Textiles (Head Office)  
 Office 2402-2403, 24-th Floor,  
 Zhongyi International Commercial Plaza,  
 1833 Zhongshan North Road, Shanghai, China  
 Zip 200061  
 Telephone: +86 (21) 5240-1156  
 www.xmfireline.com

XM Textiles Europe  
 Dariaus ir Gireno st. 42A  
 Office 510  
 Vilnius LT – 02189  
 Lithuania  
 Telephone: +370 (347) 20299  
 www.xmfireline.com

XM Textiles Spain  
 Parque Empresarial Prado del Espino  
 C/Impresores, 20, oficina A-12  
 28660 Boadilla del Monte, Madrid  
 Spain  
 Telephone: +34 91 060 28 84  
 www.xmfireline.com